



## APWA (2006) SECTION 101

### PORTLAND CEMENT CONCRETE

*Revised 09/16/2021*

1. In the Subsection 101.15 QUALITY ASSURANCE SAMPLING AND TESTING, paragraph 101.15.2.2, delete the first sentence and replace with the following:

At least one sample from each of the first three concrete loads delivered to the site shall be tested at the point of placement for slump, air content, and unit weight. Example: If a concrete pump is used, the point of placement location would be the end of the pump's outlet hose/nozzle.

One set of compressive strength test cylinders shall be obtained from one of the first three loads, as directed by SCAFCA. Beginning with the fourth load of concrete delivered to the project, one load from each sub-lot of ten (10) loads will be randomly selected for testing to include slump, air content, unit weight, cement content per cubic yard, and one set of compressive strength test cylinders. Sample requirements are subject to change at the discretion of the Engineer.

**END OF SECTION**